




# Basic Quality Statistical Summary Report

**Plant** 1210-Savannah Sand Mine  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 06/02/2025 - 06/09/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	97-100	
#8 (2.36mm)	7	100	0.0	97-100	
#16 (1.18mm)	7	99	0.7	90-100	
#30 (.6mm)	7	97	1.3	65-100	
#50 (.3mm)	7	73	3.7	35-90	
#100 (.15mm)	7	13	3.8	0-40	
#200 (75µm)	7	1.0	0.23		
Pan	7	0.0	0.00		
FM	7	1.19	0.050		
Total Moisture	7	12.2	4.00	0-6\3	0-7
D10 (ES)	7	0.13	0.016		
D50	7	0.23	0.007		
D60	7	0.26	0.010		
Cc	7	1.03	0.063		
Cu	7	2.08	0.202		



Tests: 1 D10(ES): 0.126 D15: 0.154 D30: 0.183 D50: 0.230 D60: 0.258 D85: 0.424 D90: 0.490 Cu: 2.047 Cc: 1.023

**Query**

Query Selections

Date Created 06/09/2025

Date Range 06/02/2025 - 06/09/2025

Plant Savannah Sand Mine

Sample Type Shipping